

Aristide nv
Dhr. Joris Paridaens
Nachtegaalstraat 109
2550 KONTICH

Your notice of
 24-04-2019

Your reference

Date
 16-05-2019

Analysis Report 19.02508.01

Required tests :

- ISO 105-B02 (2014)**
- ISO 12945-2 (2000)**
- EN 1021-1 (2014)**
- EN 1021-1 (2014)**

- EN 1021-2 (2014)**

- ISO 12947-2 (2016)**

- Determination of the colour fastness to light**
- Determination of the resistance to pilling - Martindale**
- Water soaking procedure**
- Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : smouldering cigarette**
- Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : match flame equivalent**
- Determination of the abrasion resistance - Martindale**

Identification number	Information given by the client	Date of receipt
T1909427	Crystal / 220 latte	24-04-2019
T1909428	Hulk / 205 off-white	24-04-2019
T1909429	Atom / 135 Marble	24-04-2019
T1909430	Lobo / 690 Midnight	24-04-2019
T1909431	Castel 780 / Hunter	24-04-2019

Bea De Paepe
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T1909429 - Atom / 135 Marble

Water soaking procedure

Date of ending the test 29-04-2019
Standard used EN 1021-1 (2014)/EN 1021-2 (2014)

Deviation from the standard -

The water soaking procedure is compatible with following standard(s):

EN 1021-1 Ann.D (2014)

EN 1021-2 Ann.D (2014)

Sample generated: T1909429_01d

Reference: T1909429_01d - Atom / 135 Marble

Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : smouldering cigarette

Date of ending the test 15-05-2019
 Standard used EN 1021-1 (2014)
 Deviation from the standard -
 Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Filling T 23140 (Recticel) - non-fire retardant foam - ± 22 kg/m³

	1 #	2 #	3 #
Smouldering criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Smoulders to extremities	no	no	no
Smoulders through thickness	no	no	no
Smoulders more than 1 hour	no	no	no
Final examination / active smouldering	no	no	no
Flaming criteria			
Occurrence of flames	no	no	no
	non-ignition	non-ignition	non-ignition

cigarette fails to smoulder its complete length

Conclusion Non-ignition

Reference: T1909429_01d - Atom / 135 Marble

Furniture - Assessment of the ignitability of upholstered furniture – Ignition source : match flame equivalent

Date of ending the test 15-05-2019
 Standard used EN 1021-2 (2014)
 Deviation from the standard -
 Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Filling T 23140 (Recticel) - non-fire retardant foam - ± 22 kg/m³
 Flame application time (s) 15

	1	2	3
Smouldering criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Smoulders to extremities	no	no	no
Smoulders through thickness	no	no	no
Smoke/heat/glowing more than 60 min	no	no	no
Final examination / active smouldering	no	no	no
Flaming criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Flames to extremities	no	no	no
Flames through thickness	no	no	no
Flaming > 120 s	no	no	no
Afterflame time (s)	0	0	1
	non-ignition	non-ignition	non-ignition

Conclusion Non-ignition